

OR APR 18 2006 2693-203

41694

2693-203

(Red)

MAR 28 2008 SS

 **Interlux**

Trilux 33

**KEEP OUT OF REACH OF CHILDREN
DANGER**

See Side Panel for Additional Precautionary Statements

**NET CONTENTS:
ONE U.S. GALLON (3.785 L)**

**YBA062
RED**

ACTIVE INGREDIENTS:	PERCENT
CUPROUS THIOCYANATE	16.95%
ZINC 2-PYRIDINETHIOL 1-OXIDE*	3.39%
INERT INGREDIENTS:	79.66%
	100.00%

COPPER AS METALLIC 8.65%
*ZINC PYRITHIONE

CONTAINS PETROLEUM DISTILLATES

EPA EST 2893-NJ-1
EPA REG NO. 2693-203

REVISER
DATE
REVIEWER
SS

TRILUX® 33

PRODUCT DESCRIPTION: TRILUX® 33 was developed for use on aluminum hulls vessels but can be used on fiberglass, wood and steel surfaces. TRILUX® 33 uses Biolux® Technology to control slime and algae growth and a resin system that allows for the controlled release of biocide. The performance of TRILUX® 33 is directly related to the amount of paint applied (Thin film thickness may lead to premature fouling). TRILUX® 33 is for use on recreational or commercial vessels below the waterline on underwater boat hulls and parts in fresh, salt and brackish water and can be brush or roller applied. Spray application is not recommended.

TRILUX® 33 is part of International Paint's globally compatible Superyacht antifouling paint system. TRILUX® 33 is compatible with all TRILUX® 33 antifouling paints regardless of country of origin. Follow the application instructions for previously painted surfaces. Tin based copolymers should be removed or sealed with a coat of Primocon YPA584.

DIRECTIONS FOR USE: It is a violation of Federal Law to use this product in a manner inconsistent with its labeling.

GENERAL APPLICATION PROCEDURES

Apply at least 2-3 full coats of TRILUX® 33 by brush or solvent resistant 3/8" nap roller. Do not apply thin coats. Keep in mind that the life of the paint is directly related to the amount of paint applied. Certain areas of the hull, such as the leading edge of the keel and rudder, the waterline and the bow stem polish faster than other areas. On these areas we suggest an additional coat of paint to insure that the TRILUX® 33 does not polish away before other areas of the bottom.

PREPARATION

BARE ALUMINUM - On small craft where sandblasting is not practical, i.e. aluminum pontoon boats, car top boats etc.; Wipe bare metal with Special Thinner 216 to remove oil and grease. Uniformly, sand surface to a bright luster with medium grit emery cloth. Wipe surface clean of dust. Immediately apply one thin coat of Viny-Lux Primewash 353/354 thinned 25% with Viny-Lux Solvent 355. Allow to dry a minimum of one hour but no more than twenty-four hours then apply Interprotect 2000E/2001E. Apply enough Interprotect 2000E/2001E to obtain a 10 mil dry film thickness. This usually takes 4-5 coats to obtain this thickness, although the amount of paint is more important than the number of coats. Be sure to follow dry times on the Interprotect 2000E/2001E label. When complete, apply at least three coats of TRILUX® 33. If dry times for Interprotect 2000E/2001E cannot be followed, use the following alternate system. Apply four coats of Primocon over the Viny-Lux Primewash. On rivets and adjacent areas, apply a minimum of 5 coats of Primocon. Finish with at least three coats of TRILUX® 33.

ALUMINUM-PREVIOUSLY PAINTED WITH ANTIFOULING PAINT: Remove incompatible antifouling paint (soft, tin based copolymers or cuprous oxide) and primer (EPOXY PRIMER MAY BE LEFT ON IF IT IS IN GOOD CONDITION) to bare aluminum and proceed with bare system above. If the TRILUX® 33 paint and primer system is in good condition, sand with 80-grit sandpaper. Wipe off sanding residue with Special Thinner 216. Any areas where the bare aluminum is exposed must be sanded with medium grit emery cloth and wiped clean. Immediately apply Primocon to bare areas. Then apply at least two additional coats of Primocon to the entire underwater surface. Apply three coats of TRILUX® 33.

ALUMINUM-PREVIOUSLY PAINTED WITH A FACTORY FINISH: Wipe surface clean with Special Thinner 216 to remove contaminants. Sand the surface with 120-grit sandpaper. Wipe the surface again with Special Thinner 216, to remove sanding residue. Immediately spot prime any bare areas with Primocon. Apply at least two full coats of Primocon (three coats to riveted areas), to the entire bottom, allowing appropriate dry times. After an overnight dry apply at least three coats of TRILUX® 33.

PREVIOUSLY PAINTED SURFACES - In Good Condition: Rinse with fresh water and allow to dry. Abrade with 80-grit sandpaper. Remove sanding residue by wiping clean with Special Thinner 216.

In Poor Condition: Remove all previous coatings using Interstrip 299E and prime the substrate.

PRIMING

All preparation for bare substrates is covered on the appropriate primer datasheet.

BARE FIBERGLASS - NO SAND SYSTEM: Clean entire surface thoroughly with Fiberglass Solvent Wash 202, changing rags frequently. Before the liquid dries, wipe clean with dry cloth. Be sure all wax and other contaminants are removed; if surface is not clean contamination will occur. Apply one thin, continuous coat of Interlux Fiberglass No-Sand Primer YPA200. Follow the primer label directions for overcoating.

BARE FIBERGLASS - SANDING SYSTEM: Be sure all wax and other contaminants are removed by cleaning the surface with Fiberglass Solvent Wash 202. Wash the surface thoroughly with a rag that has been soaked in Fiberglass Solvent Wash 202 and 80-grit sandpaper until a flat, matte finish has been obtained. Wipe off the sanding residue with Fiberglass Solvent Wash 202.

BARE WOOD: Sand entire surface thoroughly to a smooth finish with 80-grit sandpaper. Clean off the sanding residue using Special Thinner 216 on a damp rag. Prime with Primocon. Apply three coats of TRILUX® 33 antifouling.

PREVIOUSLY PAINTED FIBERGLASS AND WOOD-GOOD CONDITION: Remove all traces of loose paint and contamination by sanding the entire surface with 80-grit sandpaper. Wipe surface clean with Special Thinner 216. Apply 1-2 coats of Primocon.

UNDERWATER METALS INCLUDING SHAFTS, PROPELLERS, TRIM TABS, STRUTS AND THRU-HULL FITTINGS: These areas require special attention to initial surface preparation in order to improve adhesion. Treat these areas the same as bare aluminum. The longevity of this system will probably not be equal to that of the remainder of the boat due to the RPMs these parts withstand. For more details contact Interlux Technical Service at 1-800-468-7589.

APPLICATION

For applications by residential (non-commercial) users:

- Do not apply by aerosol spray
- Do not apply more than one coat of this product within 24 hours
- Apply only in outdoor, non-enclosed spaces

Apply three coats of TRILUX® 33 by brush or roller.

THINNER: Special Thinner 216

COVERAGE: 400 sq. ft./Gallon

BARE FIBERGLASS: Apply a minimum of three coats of TRILUX® 33 antifouling.

BARE WOOD: Apply the first coat of TRILUX® 33 reduced with Special Thinner 216 (10% maximum) to penetrate the porous grain. Fill seams with Seams Compound 30. Apply second and third coats of TRILUX® 33 antifouling unthinned.

PREVIOUSLY PAINTED FIBERGLASS AND WOOD - GOOD CONDITION: Apply three coats of Trilux 33 antifouling.

NOTE: TRILUX® 33 antifouling white may show a green patina at the waterline, especially when applied in thin coats. This patina does not affect antifouling performance.

IMPORTANT: Do not apply Primocon or TRILUX® 33 above the low waterline.

PRECAUTIONARY STATEMENTS HAZARDS TO HUMANS AND DOMESTIC ANIMALS KEEP OUT OF REACH OF CHILDREN

DANGER

Danger. Causes skin burns. Causes substantial but temporary eye injury. May be fatal if inhaled. Harmful if swallowed. Do not get in eyes, on skin, or on clothing. Do not breathe dust, vapor, spray mist. Wash thoroughly with soap and water after handling and before eating, drinking, or using tobacco. Remove contaminated clothing and wash clothing before reuse.

Residential (non-commercial) users are advised to wear chemical resistant gloves, protective eyewear (goggles, safety glasses, or face shield), long sleeved shirt and long pants, socks and shoes. In addition to these minimum PPE, commercial users must wear a disposable coverall with hood and chemical resistant footwear.

While removing existing paint by sanding or blasting, or applying new antifouling paint, commercial users must wear a respirator with an organic vapor removing cartridge with a prefilter approved for pesticides (MSHA/NIOSH approval number prefix TC-23C), or a canister approved for pesticides (MSHA/NIOSH approval number TC-14G), or a NIOSH approved full face respirator with an organic vapor removing cartridge with a P-100 prefilter. Residential (non-commercial) users are advised to wear the same respirators, cartridges, and prefilters as required by commercial users.

STATEMENT OF PRACTICAL TREATMENT

If Swallowed:

- Immediately call a poison control center or doctor.
- Do not induce vomiting unless told to do so by a poison control center or doctor.
- Do not give any liquid to the person.
- Do not give anything by mouth to an unconscious person.

If on skin or clothing:

- Take off contaminated clothing.
- Rinse skin immediately with plenty of water for 15-20 minutes
- Call a poison control center or doctor for treatment advice.

If Inhaled:

- Move person to fresh air.
- If person is not breathing, call 911 or an ambulance, then give artificial respiration, preferably mouth-to-mouth if possible.
- Call a poison control center or doctor for further treatment advice.

If in eyes:

- Hold eye open and rinse slowly and gently with water for 15-20 minutes.
- Remove contact lenses, if present, after the first 5 minutes, then continue rinsing eye.
- Call a poison control center or doctor for treatment advice.

Other: Have the product container or label with you when calling a poison control center or doctor or going for treatment.

Note to Physician: Contains petroleum distillate - vomiting may cause aspiration pneumonia.

ENVIRONMENTAL HAZARDS: This material is toxic to fish. Do not apply directly to water by cleaning of equipment or disposal of wastes. Do not allow chips and dust generated during paint removal to enter water. Dispose of paint debris in an approved landfill. Do not discharge effluent containing this product into lakes, streams, ponds, estuaries, oceans or other waters unless in accordance with the requirements of a National Pollution Discharge Elimination System (NPDES) permit and the permitting authority has been notified in writing prior to discharge. Do not discharge effluent to sewer system without previously notifying the local sewage treatment plant authority. For guidance contact your State Water Board or Regional Office of the EPA.

PHYSICAL OR CHEMICAL HAZARD: FLAMMABLE! Keep away from heat and open flame.

STORAGE AND DISPOSAL: Do not contaminate water, food or feed by storage or disposal.

PESTICIDE STORAGE: Keep away from heat and open flame. Keep product container tight and upright to prevent leakage. Keep container closed when not in use. Absorb and dispose of spillages in accordance with local applicable regulations.

PESTICIDE DISPOSAL: Pesticide wastes are toxic. Open dumping is prohibited. Pesticide, spray mixture, or rinse that cannot be used or chemically reprocessed should be disposed of according to procedures approved by Federal, State or local disposal authorities.

CONTAINER DISPOSAL: Triple rinse (or equivalent) and dispose of in an approved landfill. Consult Federal, State or local disposal authorities for approved alternative procedures.

FOR CHEMICAL EMERGENCY, SPILL, LEAK, EXPOSURE OR ACCIDENT, CALL TOLL FREE: CHEMTREC 1-800-424-9300 (DAY OR NIGHT)
MEDICAL ADVISORY: CONTACT YOUR LOCAL POISON CONTROL CENTER OR CALL 1-800-654-6813.
Rev. 2/05

Interlux, Trilux and Biolux are registered trademarks of Akzo Nobel.

Interlux

International Paint LLC

2270 Morris Ave., Union, NJ 07083 • 908-686-1300



AKZO NOBEL

DISCLAIMER: The performance of any marine paint or coating depends on many factors outside the control of International Paint LLC including surface preparation, proper application, and environmental conditions. International Paint LLC cannot guarantee this product's suitability for your particular purpose or application. LIMITED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE AND OF MERCHANTABILITY ARE EXCLUDED. INTERNATIONAL PAINT LLC SHALL NOT, UNDER ANY CIRCUMSTANCES, BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES. By purchase or use of this product, buyer agrees that the sole and exclusive remedy, if any, is limited to the refund of the purchase price or replacement of the product at International Paint LLC's option.