

DISCLAIMER: The performance of any marine paint or coating depends on many factors outside the control of INTERNATIONAL PAINT, LLC, including surface preparations, proper application and environmental conditions. Therefore, INTERNATIONAL PAINT, LLC, cannot guarantee the suitability of this product for your particular purpose of application. To the extent consistent with applicable law, INTERNATIONAL PAINT, LLC, EXPRESSLY DISCLAIMS ALL REPRESENTATIONS AND WARRANTIES INCLUDING, WITHOUT LIMITATION, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE or otherwise that extend beyond the statements made on this label, and shall not be liable for special, incidental, or consequential damages resulting from the use or handling of this product. The exclusive remedy being the replacement of this product, the use and/or handling is contrary to label instructions.

AkzoNobel



DUAL  
RESIN  
TECHNOLOGY

# FIBERGLASS BOTTOMKOTE® NT

Dual resin technology  
Universal for use on all power and sailboats  
Durable coating yet minimizes paint build up

KEEP OUT OF REACH OF CHILDREN  
WARNING

See Side Panel for Additional Precautionary Statements

YBB349  
RED

ONE U.S. GALLON  
(3.785 L)

ACTIVE INGREDIENT  
CUPROUS OXIDE 25.00%  
OTHER INGREDIENTS 75.00%  
100.00%

COPPER AS METALLIC 22.20%  
CONTAINS PETROLEUM DISTILLATES

EPA ESTABLISHMENT NO. 2693-TX-1  
EPA REGISTRATION NO. 2693-228

## PRECAUTIONARY STATEMENTS HAZARDS TO HUMANS AND DOMESTIC ANIMALS WARNING

May be fatal if swallowed or inhaled. Causes eye irritation. Harmful if absorbed through skin. Avoid contact with skin, eyes or clothing. Wear protective clothing such as gloves, long-sleeved cotton shirt, long pants and hat. Do not breathe vapor or spray mist. While painting or sanding or sandblasting boat surfaces, wear a NIOSH approved particulate filter with any N, R, P filter with NIOSH approval number prefix TC-84A.; or a NIOSH approved powered air purifying respirator with an HE filter with NIOSH approval number prefix TC-21C. Remove contaminated clothing and wash before reuse. Wash thoroughly with soap and water after handling and before eating, drinking, chewing gum, using tobacco, or using the toilet. Remove contaminated clothing and wash clothing before reuse.

### FIRST AID

#### If Swallowed:

- Call a poison control center or doctor immediately for treatment advice.
- Have person sip a glass of water if able to swallow.
- Do not induce vomiting unless told to do so by a poison control center or doctor.
- Do not give anything by mouth to an unconscious person.

#### If inhaled:

- Move person to fresh air.
- If person is not breathing, call 911 or an ambulance, then give artificial respiration, preferably mouth-to-mouth if possible.
- Call a poison control, center or doctor for further treatment advice.

#### If in eyes:

- Hold eye open and rinse slowly and gently with water for 15-20 minutes.
- Remove contact lenses, if present, after the first 5 minutes, then continue rinsing eye.
- Call a poison control center or doctor for treatment advice.

#### If on skin or clothing:

- Take off contaminated clothing.
- Rinse skin immediately with plenty of water for 15-20 minutes.
- Call a poison control center or doctor for treatment advice.

Have the product container or label with you when calling a poison control center or doctor or going for treatment. For medical emergencies, call the poison control center at 1-800-222-1222. For general information on this product, contact the National Pesticides Information Center (NPIC) at 1-800-858-7378, Monday through Friday, 8 AM to 12 PM PST, or at <http://npic.orst.edu>.

**Note to Physician:** Contains petroleum distillate – vomiting may cause aspiration pneumonia.

### ENVIRONMENTAL HAZARDS

This material is toxic to fish. Do not apply directly to water by cleaning of equipment or disposal of wastes. Do not allow chips and dust generated during paint removal to enter water. Dispose of paint debris in an approved landfill. Do not discharge effluent containing this product into lakes, streams, ponds, estuaries, oceans or other waters unless in accordance with the requirements of a National Pollutant Discharge Elimination System (NPDES) permit and the permitting authority has been notified in writing prior to discharge. Do not discharge effluent to sewer systems without previously notifying the local sewage treatment plant authority. For guidance contact your State Water Board or Regional Office of the EPA.

### PHYSICAL OR CHEMICAL HAZARD

Flammable. Keep away from heat and open flame.

### STORAGE AND DISPOSAL

Do not contaminate water, food or feed by storage or disposal.

**STORAGE:** Exposure to air and extremes of temperature must be avoided. Keep the container firmly closed. Keep out of direct sunlight. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition.


**PESTICIDE DISPOSAL:** Pesticide wastes are acutely hazardous. Improper disposal of excess pesticide, spray mixture or rinsate is a violation of Federal Law. If these wastes cannot be disposed of by use according to label instructions, contact your State Pesticide or Environmental Control Agency, or the Hazardous Waste representative at the nearest EPA Regional Office for guidance.

**CONTAINER HANDLING:** Nonrefillable container. Do not reuse or refill this container. Prior to container disposal, allow any remaining paint residue in the container to air dry. Dispose of the container in accordance with Federal, State or local disposal regulations.

International Paint LLC, 6001 Antoine Dr. Houston,  
TX USA 77091 • 713-682-1711

Interlux and the AkzoNobel logo are trademarks  
of AkzoNobel. © AkzoNobel 2020.

YBB349/GL ZU0230qc



## FIBERGLASS BOTTOMKOTE® NT

**PRODUCT DESCRIPTION:** Fiberglass Bottomkote NT uses a dual resin technology that provides a universal durable, fast dry antifouling paint that delivers the benefits of both hard and polishing antifouling paints for use on all power and sailboats. The universal formula of Fiberglass Bottomkote NT has durability of a traditional hard paint but has a slow polishing mechanism built-in that continuously smooths and renews the active surface avoiding the heavy build-up of paint layers much like a polishing paint. The fast dry formula allows the boat to be painted and launched in the same day. Fiberglass Bottomkote NT provides clean stable colors for effective season-long protection. Fiberglass Bottomkote NT is recommended for use on the underwater areas of fiberglass, wood, and properly primed metal (except aluminum) boat hulls. It can be used in fresh, salt and brackish waters.

**DIRECTIONS FOR USE:** It is a violation of Federal law to use this product in a manner inconsistent with its labeling.

**COMPATIBILITY:** Fiberglass Bottomkote NT can be applied over most other antifouling paints provided the old coating is tightly adhered, is in sound condition and has been thoroughly sanded with 80 grit wet-or-dry sandpaper. Fiberglass Bottomkote NT can be applied by brush, roller or spray.

**V.O.C.:** Less than 465 grams/liter (3.9 lbs./gallon).

**THINNER:** Interlux Special Thinner 216 or Interlux Brush Ease 433.

**CLEAN UP:** Special Thinner 216 or Brush Ease 433.

**APPLICATION TEMPERATURE:** 50°F (10°C)\* and above (air and hull).

### ESTIMATED DRY TIMES:

| Temperature<br>°F (°C) | Touch<br>Dry | Overcoating Time<br>Minimum | Immersion Time |         |
|------------------------|--------------|-----------------------------|----------------|---------|
|                        |              |                             | Minimum        | Maximum |
| 50°F (10°C)            | 3 Hours      | 6 Hours                     | 12 Hours       | 60 Days |
| 60°F (15°C)            | 2 Hours      | 4 Hours                     | 10 Hours       | 60 Days |
| 75°F (24°C)            | 1 Hour       | 2 Hours                     | 6 Hours        | 60 Days |
| 95°F (35°C)            | 30 Minutes   | 1 Hour                      | 3 Hours        | 60 Days |

\*If the air temperature falls below 50°F (10°C) during the dry time extend the dry time by 12 hours minimum.

### PREPARATION

#### PREVIOUSLY PAINTED SURFACES - GOOD CONDITION:

Remove all traces of loose paint and contamination by sanding the entire surface with 80 grit wet-or-dry sandpaper; wipe surface clean with Special Thinner 216. Apply at least 2 coats of Fiberglass Bottomkote NT.

#### PREVIOUSLY PAINTED SURFACES - POOR CONDITION:

Completely remove all old antifouling paint, using Interlux Interstrip 299E for fiberglass, and wood, and by sandblasting or grinding to near white metal for steel. Follow application systems below.

#### BARE FIBERGLASS:

It is very important that bare fiberglass be properly prepared to prevent delamination of the antifouling paint. Remove mold release wax and surface contamination by using one of the following Interlux products: Fiberglass Surface Prep YMA601 or Fiberglass Solvent Wash 202 following the product label instructions. Fill any surface imperfections with Interlux Waterite YAV135 following the label instructions. After the surface has been properly cleaned, proceed with one of the application systems below.

### APPLICATION SYSTEMS

#### BARE FIBERGLASS - NO SAND SYSTEM:

Clean the surface following the preparation procedure above. Apply one coat, of Interlux InterProtect® 2000 following the label instructions for applying the primer and over coating with antifouling paint. Apply two coats of Fiberglass Bottomkote NT, allowing for the appropriate dry times.

#### BARE FIBERGLASS - SANDING SYSTEM:

Clean the surface following the preparation procedure above for bare fiberglass. Sand the entire surface with 80-grit sandpaper until a flat matte finish is obtained. Wipe the sanding residue off the surface with Fiberglass Solvent Wash 202. Sand and wipe clean. Apply two coats of Fiberglass Bottomkote NT allowing for appropriate dry times.

#### BARE FIBERGLASS - BLISTER PREVENTION SYSTEM:

Apply the InterProtect system for the prevention of blisters. Contact the Interlux Technical Service Department at 1-800-468-7589 or visit [yachtpaint.com](http://yachtpaint.com) for complete instructions on the application of the InterProtect system.

#### BARE WOOD:

Sand the entire surface with 80-grit sandpaper. Wipe the sanding residue off the surface with Special Thinner 216. Apply the first coat of Fiberglass Bottomkote NT thinned 10% with Special Thinner 216 or Brush-Ease 433. Fill seams with Interlux Seam Compound 30 (if necessary). Apply two more coats of Fiberglass Bottomkote NT unthinned, allowing for the appropriate dry times.

#### UNDERWATER METALS:

Contact the Interlux Technical Service Department at 1-800-468-7589 for full information on how to properly prime underwater metals or steel hulls. More systems and information available on [www.interlux.com](http://www.interlux.com). DO NOT USE ON ALUMINUM.

Color difference may occur between actual paint and color swatch on front of can.

ZU0230qc

interlux.com