

DISCLAIMER: The performance of any marine paint or coating depends on many factors outside the control of International Paint LLC, including surface preparation, proper application, and environmental conditions. Therefore, International Paint LLC cannot guarantee the product's suitability for your particular purpose or application. IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE AND OF MERCHANTABILITY ARE EXCLUDED. INTERNATIONAL PAINT LLC SHALL NOT, UNDER ANY CIRCUMSTANCES, BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES. By purchase or use of this product, buyer agrees that the sale and exclusive remedy, if any, is limited to the refund of the purchase price or replacement of the product at International Paint LLC's option.

NEW
APR 28 2011
DATE REVIEWER
MML



Ultra™

High Copper Antifouling for Ultimate Protection
Hard, Long Lasting Formula for Fiberglass, Wood and Steel


ACTIVE INGREDIENTS:	PERCENT
CUPROUS OXIDE	55.00%
N-CYCLOPROPYL-N'-(1,1-DIMETHYLETHYL)-6-(METHYLTHIO)-1,3,5-TRIAZINE-2,4-DIAMINE	0.98%
INERT INGREDIENTS	44.02%
	<hr/> 100.00%

COPPER AS METALLIC 48.8%
CONTAINS PETROLEUM DISTILLATE
EPA EST 2693-NJ-1
EPA REG NO. 2693-212

NET CONTENTS:
ONE U.S. GALLON (3.785 L)

KEEP OUT OF REACH OF CHILDREN
CAUTION
See Side Panel for Additional Precautionary Statements.

3779F
BLACK



yachtpaint.com

OR MAY 13 2011 2693-212

55938

ULTRA™

PRODUCT DESCRIPTION: This product is a hard, durable, high-strength antifouling paint for use in severe fouling areas. This product provides excellent long-term protection from shell and weed fouling and uses Biolux® technology to block slime. The fast dry formula of this product allows your boat to be painted and launched in the same day. This product is recommended for use wherever the fouling challenge is severe, and can be used in fresh, salt and brackish water on fiberglass, wood and properly primed metal boat hulls and parts. This product can be applied by brush, roller or spray. This product has excellent color stability and resists changing color at the waterline.

DIRECTIONS FOR USE:

It is a violation of Federal Law to use this product in a manner inconsistent with its labeling.

COMPATIBILITY: Ultra can be applied over any other hard antifouling paint after sanding the surface. Soft antifouling paints will need to be removed or overcoated with Primocon® before applying this product.

V.O.C.: Less than 330 grams/liter (2.75 lbs./gallon) **THEORETICAL COVERAGE:** 495 sq. ft./ gallon yields 2 mils dry film thickness.

THINNER: SPECIAL THINNER 216 or BRUSH-EASE 433 **DRY TIMES:** Touch dry - 1 hour
77°F (25°C) Dry to overcoat - 2 hours minimum
Dry to launch - 8 hours minimum

THINNING: Thin only when necessary
Do not exceed 10% maximum. 60 days maximum

APPLICATION TEMPERATURES: 50°F (10°C)* and above (air and hull)

*If either the air temperature falls below 50°F (10°C) during the dry time extend the dry times to 12 hours minimum.

APPLICATION SYSTEMS

PREVIOUSLY PAINTED - GOOD CONDITION: Remove all traces of loose paint and contamination by sanding the entire surface with 80 grit sandpaper; wipe surface clean with Special Thinner 216. Apply at least 2 coats of this product.

PREVIOUSLY PAINTED - POOR CONDITION: Completely remove all old antifouling paint, using Interstrip® 299E. Sand and wipe clean with Fiberglass Solvent Wash 202.

BARE FIBERGLASS: It is very important that bare fiberglass be properly prepared to prevent delamination of the antifouling paint. Begin by scrubbing the surface thoroughly with a stiff brush using Interlux All-Purpose Boat Soap and water to remove loose dirt and contamination. Flush with fresh water to remove the soap residue and allow to dry. Remove mold release wax using one of the following Interlux products. Fiberglass Surface Prep YMA601 or Fiberglass Solvent Wash 202 following the product label instructions. To be certain that all of the contamination has been removed, run water over the surface. If the water beads up or separates, clean again. When the water sheets off, all contamination has been removed. After the surface has been properly cleaned, proceed with one of the application systems below.

BARE FIBERGLASS - NO SAND SYSTEM: Clean the surface following the preparation procedure above. Apply one coat of Interlux InterProtect® 2000, or Fiberglass No-Sand Primer YPA200 following the label instructions for applying the primer and overcoating with antifouling paint. Apply two coats of this product, allowing for the appropriate dry times.

BARE FIBERGLASS - SANDING SYSTEM: Clean the surface following the preparation procedure above. Sand the entire surface with 80-grit sandpaper and wipe clean with Fiberglass Solvent Wash 202 to remove sanding residue. Repair any surface imperfections with Watertite YAV135. Sand and wipe clean. Apply two coats of this product allowing for appropriate dry times.

BARE WOOD: Sand the entire surface with 80-grit sandpaper, wipe surface clean with Interlux Special Thinner 216. Repair imperfections with Watertite YAV135. Sand and wipe clean. Apply the first coat of this product thinned 10% with Special Thinner 216 or Brush-Ease 433. Fill seams with Seam Compound 30 (if necessary). Apply two more coats of this product unthinned, allowing appropriate dry times.

UNDERWATER METALS: Contact the Interlux Technical Service Department at 1-800-468-7589 for full information on how to properly prime underwater metals. DO NOT USE ON ALUMINUM.

PRECAUTIONARY STATEMENTS HAZARDS TO HUMANS AND DOMESTIC ANIMALS CAUTION

Harmful if absorbed through skin or inhaled. Causes moderate eye irritation. Avoid contact with eyes, skin or clothing. Wear protective clothing such as gloves, long-sleeved cotton shirt, long pants, and hat. Avoid breathing spray mist. While spraying paint or sanding or sand blasting boat surfaces, wear a mask or a respirator jointly approved by the Mining Safety & Health Administration and the National Institute of Occupational Safety & Health. Wash thoroughly with soap and water after handling. Remove contaminated clothing and wash clothing before reuse. May pose an aspiration pneumonia hazard.

FIRST AID

If Swallowed:

- Call a Poison Control Center or doctor immediately for treatment advice.
- Have a person sip a glass of water if able to swallow.
- Do not induce vomiting unless told to do so by a Poison Control Center or doctor.
- Do not give anything by mouth to an unconscious person.

If In Eyes:

- Hold eye open and rinse slowly and gently with water for 15-20 minutes.
- Remove contact lenses, if present, after the first 5 minutes, then continue rinsing eyes.
- Call a Poison Control Center or doctor for treatment advice.

If On Skin And Clothing:

- Take off contaminated clothing.
- Rinse skin immediately with plenty of water for 15-20 minutes.
- Call a Poison Control Center or doctor for treatment advice.

If Inhaled:

- Move person to fresh air.
- If person is not breathing, call 911 or an ambulance, give artificial respiration preferably mouth-to-mouth if possible.

• Call a Poison Control Center or doctor for further treatment advice.

In case of emergency call 1-800-854-6813. Have the product container or label with you when calling a Poison Control Center or doctor or going in for treatment.

ENVIRONMENTAL HAZARD

This material is toxic to fish. Do not apply directly to water by cleaning of equipment or disposal of wastes. Do not allow chips and dust generated during paint removal to enter water. Dispose of paint debris in an approved landfill. Do not discharge effluent containing this product into lakes, streams, ponds, estuaries, oceans and other waters unless in accordance with the requirements of a National Pollution Discharge Elimination System (NPDES) permit and the permitting authority has been notified in writing prior to discharge. Do not discharge effluent to sewer system without previously notifying the local sewage treatment plant authority. For guidance contact your State Water Board or Regional Office of the EPA.

PHYSICAL OR CHEMICAL HAZARD: Combustible. Do not use or store near heat or open flame.

STORAGE AND DISPOSAL: Do not contaminate water, food or feed by storage or disposal. Open dumping is prohibited.

PESTICIDE DISPOSAL: Pesticide wastes are acutely hazardous. Improper disposal of excess pesticide, spray mixture or rinsate is a violation of Federal Law. If these wastes cannot be disposed of by use according to label instructions, contact your State Pesticide or Environmental Control Agency, or the Hazardous Waste representative at the nearest EPA Regional Office for guidance.

CONTAINER DISPOSAL: Nonrefillable container. Do not reuse or refill this container. Triple rinse as follows: Empty the remaining contents into application equipment or a mix tank and drain for 10 seconds after the flow begins to drip. Fill the container ¼ full with water and recap. Shake for 10 seconds. Pour rinsate into application equipment or a mix tank or store rinsate for later use or disposal. Drain for 10 seconds after the flow begins to drip. Repeat this procedure two more times.

FOR CHEMICAL EMERGENCY, SPILL, LEAK, EXPOSURE OR ACCIDENT, CALL TOLL FREE: CHEMTREC 1-800-424-9300 (DAY OR NIGHT) MEDICAL ADVISORY: CONTACT YOUR LOCAL POISON CONTROL CENTER OR CALL 1-800-854-6813.

Label Rev. 080211

✳️, 'Ultra', 'Biolux' and 'Interlux' are registered trademarks of Akzo Nobel.

✳️ Interlux.

International Paint LLC.
2270 Morris Ave., Union, NJ 07083 • 908-686-1300