

NAUTICAL™

ANTIFOULING

PROGUARD ABLATIVE

Performance, value and reliability
Season-long protection in moderate to high fouling waters

**KEEP OUT OF REACH OF CHILDREN
WARNING**

SEE SIDE PANEL FOR ADDITIONAL
PRECAUTIONARY STATEMENTS




AkzoNobel

ACTIVE INGREDIENT:
CUPROUS OXIDE 41.97%
INERT INGREDIENTS 58.03%

COPPER AS METALLIC 37.11%
CONTAINS PETROLEUM DISTILLATES
EPA EST. NO. 2693-TX-1
EPA REG NO. 2693-142

**NET CONTENTS:
ONE GALLON
(3.785 LITERS)**



PROGUARD ABLATIVE

PRODUCT DESCRIPTION

ProGuard Ablative is performance, value and reliability all in one. ProGuard Ablative is an all-purpose, low V.O.C. antifouling paint formulated to erode away with use reducing paint build-up. ProGuard Ablative provides season-long protection in moderate to high fouling waters and can be applied directly over most properly prepared antifouling paints. Recommended for use on the underwater areas of fiberglass, wood, and properly primed metal (except aluminum) boat hulls and can be used in fresh, salt and brackish waters.

DIRECTIONS FOR USE

It is a violation of Federal Law to use this product in a manner inconsistent with its labeling. **NOTE:** Colors may fade or change above the waterline. Stir well before and during use, can be applied by brush, roller or spray. **Do not use on aluminum.** **COMPATIBILITY:** ProGuard Ablative can be applied over most other antifouling paints provided the old coating is tightly adhered, is in sound condition and has been thoroughly sanded with 80 grit wet-or-dry sandpaper.

V.O.C.: Less than 330 grams/liter (2.75lbs./gal.)

THEORETICAL COVERAGE: 455 sq. ft./gal at 3.6 mils WFT and 2 mils DFT.

CLEAN UP: Acetone or Xylene¹.

THINNER: Xylene² (thin only when necessary, do not exceed 10% by volume).

APPLICATION TEMPERATURE: 50°F (10°C)* and above (air and hull).

*If the air temperature falls below 50° F (10° C) during the dry time extend the dry times by 12 hours minimum.

ESTIMATED DRY TIMES:

Temp °F (°C)	Touch Dry	Overcoating Time		Immersion Time	
		Minimum	Maximum	Minimum	Maximum
50°F (10°C)	3 Hours	12 Hours	16 Hours	16 Hours	60 Days
77°F (25°C)	2 Hours	6 Hours	16 Hours	16 Hours	60 Days
95°F (35°C)	1 Hour	4 Hours	16 Hours	16 Hours	60 Days

PREPARATION/APPLICATION

BARE FIBERGLASS: Scrub the surface thoroughly with a stiff brush using soap and water. Flush with fresh water to remove the soap residue and allow surface to dry. Remove mold release wax and surface contamination by wiping down the surface with Xylene¹ using the two-rag method. Fill any surface imperfections with approved filler for underwater use. Sand the entire surface with 80-grit sandpaper until a flat matte finish is obtained. Wipe the sanding residue off the surface with Xylene¹ using the two-rag method. Apply two coats of ProGuard Ablative allowing for appropriate dry times.

PREVIOUSLY PAINTED SURFACE - GOOD CONDITION: Remove all traces of loose paint by sanding the entire surface with 80 grit wet-or-dry sandpaper; wipe surface clean with Xylene¹ using the two-rag method before and after sanding. Apply two coats of ProGuard Ablative allowing for appropriate dry times.

PREVIOUSLY PAINTED SURFACE - POOR CONDITION: Completely remove old antifouling paint, after all old antifouling paint has been completely removed, sanding the entire surface with 80 grit wet-or-dry sandpaper; wipe surface clean with Xylene¹ using the two-rag method before and after sanding. Apply two coats of ProGuard Ablative allowing for appropriate dry times.

BARE WOOD: Sand the entire surface with 80 grit wet-or-dry sandpaper; wipe surface clean with Xylene¹ using the two-rag method before and after sanding. Apply the first coat of ProGuard Ablative thinned 10% with Xylene². Apply two finish coats of ProGuard Ablative allowing for appropriate dry times.

UNDERWATER METALS: Apply an approved underwater metal primer as per manufacturer's instructions. Apply two coats of ProGuard Ablative allowing for appropriate dry times.

Do not use on aluminum.

MAINTENANCE

Antifouling are not effective under all conditions. Pollution, usage and natural occurrences can adversely affect an antifouling paint's performance. Therefore, we strongly suggest that the antifouling paints are checked regularly to make sure it is clean and that no growth is occurring. The less a boat is used, and the longer the idle periods are the higher the chance of fouling. Properly functioning antifouling paints will repel hard growth and requires only occasional light wiping with a soft cloth or Scotch-Brite™ pad to remove slime. Aggressive cleaning of antifouling paints, using tools such as scrubbing pads and brushes, will shorten the effective life of the paint, and should only be used if necessary.

¹ May not be an approved solvent for use in all areas.

² Thinning of this product may affect the V.O.C. compliance of this product.

Please consult your local government regulations for recommendations for volatile organic compound (VOC) limits.

PRECAUTIONARY STATEMENTS HAZARDS TO HUMANS AND DOMESTIC ANIMALS WARNING

Causes eye irritation. Harmful if absorbed through skin. Avoid contact with skin, eyes or clothing. Wear protective clothing such as gloves, long-sleeved cotton shirt, long pants and hat. May be fatal if swallowed or inhaled. Do not breathe vapor or spray mist. While spraying paint or sanding or sandblasting boat surfaces, wear a mask or a respirator jointly approved by the Mining Enforcement and Safety Administration and the National Institute for Occupational Safety and Health. Remove contaminated clothing and wash before reuse. Wash thoroughly with soap and water after handling.

FIRST AID

If Swallowed:

- Immediately call a poison control center or doctor
- Do not induce vomiting unless told to do so by a poison control center or doctor
- Do not give any liquid to the person
- Do not give anything by mouth to an unconscious person

If on skin or clothing:

- Take off contaminated clothing
- Rinse skin immediately with plenty of water for 15-20 minutes
- Call a poison control center or doctor for treatment advice

If inhaled:

- Move person to fresh air
- If person is not breathing, call 911 or an ambulance, then give artificial respiration, preferably mouth-to-mouth if possible
- Call a poison control center or doctor for further treatment advice

If in eyes:

- Hold eye open and rinse slowly and gently with water for 15-20 minutes
- Remove contact lenses, if present, after the first 5 minutes, then continue rinsing the eye
- Call a poison control center or doctor for treatment advice

Other: Have the product container or label with you when calling a poison control center or doctor or going for treatment.

Note to Physician: Contains petroleum distillate - vomiting may cause aspiration pneumonia.

ENVIRONMENTAL HAZARDS

This material is toxic to fish. Do not apply directly to water by cleaning of equipment or disposal of wastes. Do not allow chips and dust generated during paint removal to enter water. Dispose of paint debris in an approved landfill. Do not discharge effluent containing this product into lakes, streams, ponds, estuaries, oceans and other waters unless in accordance with the requirements of a National Pollution Discharge Elimination System (NPDES) permit and the permitting authority has been notified in writing prior to discharge. Do not discharge effluent to sewer systems without previously notifying the local sewage treatment plant authority. For guidance, contact your State Water Board or Regional Office of the EPA.

PHYSICAL OR CHEMICAL HAZARD

Flammable. Keep away from heat, sparks or open flames.

STORAGE AND DISPOSAL

Do not contaminate water, food or feed by storage or disposal. Open dumping is prohibited.

PESTICIDE DISPOSAL: Pesticide wastes are acutely hazardous. Improper disposal of excess pesticide, spray mixture or rinsate is a violation of Federal law. If these wastes cannot be disposed of by use according to label instructions, contact your State Pesticide or Environmental Control Agency, or the Hazardous Waste representative at the nearest EPA Regional Office for guidance.

CONTAINER DISPOSAL: Nonrefillable container. Do not reuse or refill this container. Triple rinse as follows: Empty the remaining contents into application equipment or a mix tank and drain for 10 seconds after the flow begins to drip. Fill the container ¼ full with water and recap. Shake for 10 seconds. Pour rinsate into application equipment or a mix tank or store rinsate for later use or disposal. Drain for 10 seconds after the flow begins to drip. Repeat this procedure two more times.

International Paint LLC
6001 Antoine Drive
Houston, TX USA
77091 • 713-682-1711

nauticalpaint.com

BLACK NAU993

DISCLAIMER: The performance of any marine paint or coating depends on many factors outside the control of International Paint LLC, including surface preparation, proper application, and environmental conditions. Therefore, International Paint LLC cannot guarantee this product's suitability for your particular purpose or application. IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE AND OF MERCHANTABILITY ARE EXCLUDED. INTERNATIONAL PAINT LLC SHALL NOT, UNDER ANY CIRCUMSTANCES, BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES. By purchase or use of this product, buyer agrees that the sole and exclusive remedy, if any, is limited to the refund of the purchase price or replacement of the product at International Paint LLC's option.

NAUTICAL™

ANTIFOULING PROGUARD ABLATIVE

Performance, value and reliability
Season-long protection in moderate to high fouling waters

**KEEP OUT OF REACH OF CHILDREN
WARNING**

SEE SIDE PANEL FOR ADDITIONAL
PRECAUTIONARY STATEMENTS




AkzoNobel

BLUE NAU990

ACTIVE INGREDIENT:
CUPROUS OXIDE 41.97%
INERT INGREDIENTS 58.03%

COPPER AS METALLIC 37.11%
CONTAINS PETROLEUM DISTILLATES

EPA EST. NO. 2693-TX-1
EPA REG NO. 2693-142



**NET CONTENTS:
ONE GALLON
(3.785 LITERS)**

PROGUARD ABLATIVE

PRODUCT DESCRIPTION

ProGuard Ablative is performance, value and reliability all in one. ProGuard Ablative is an all-purpose, low V.O.C. antifouling paint formulated to erode away with use reducing paint build-up. ProGuard Ablative provides season-long protection in moderate to high fouling waters and can be applied directly over most properly prepared antifouling paints. Recommended for use on the underwater areas of fiberglass, wood, and properly primed metal (except aluminum) boat hulls and can be used in fresh, salt and brackish waters.

DIRECTIONS FOR USE

It is a violation of Federal Law to use this product in a manner inconsistent with its labelling. **NOTE:** Colors may fade or change above the waterline. Stir well before and during use, can be applied by brush, roller or spray. **Do not use on aluminum.**

COMPATIBILITY: ProGuard Ablative can be applied over most other antifouling paints provided the old coating is tightly adhered, is in sound condition and has been thoroughly sanded with 80 grit wet-or-dry sandpaper.

V.O.C.: Less than 330 grams/liter (2.75lbs./gal.)

THEORETICAL COVERAGE: 455 sq. ft./gal at 3.6 mils WFT and 2 mils DFT.

CLEAN UP: Acetone or Xylene¹.

THINNER: Xylene² (thin only when necessary, do not exceed 10% by volume).

APPLICATION TEMPERATURE: 50°F (10°C)* and above (air and hull).

*If the air temperature falls below 50° F (10° C) during the dry time extend the dry times by 12 hours minimum.

ESTIMATED DRY TIMES:

Temp °F (°C)	Touch Dry	Overcoating Time		
		Minimum	Minimum	Maximum
50°F (10°C)	3 Hours	12 Hours	16 Hours	60 Days
77°F (25°C)	2 Hours	6 Hours	16 Hours	60 Days
95°F (35°C)	1 Hour	4 Hours	16 Hours	60 Days

PREPARATION/APPLICATION

BARE FIBERGLASS: Scrub the surface thoroughly with a stiff brush using soap and water. Flush with fresh water to remove the soap residue and allow surface to dry. Remove mold release wax and surface contamination by wiping down the surface with Xylene¹ using the two-rag method. Fill any surface imperfections with approved filler for underwater use. Sand the entire surface with 80-grit sandpaper until a flat matte finish is obtained. Wipe the sanding residue off the surface with Xylene¹ using the two-rag method. Apply two coats of ProGuard Ablative allowing for appropriate dry times.

PREVIOUSLY PAINTED SURFACE - GOOD CONDITION: Remove all traces of loose paint by sanding the entire surface with 80 grit wet-or-dry sandpaper; wipe surface clean with Xylene¹ using the two-rag method before and after sanding. Apply two coats of ProGuard Ablative allowing for appropriate dry times.

PREVIOUSLY PAINTED SURFACE - POOR CONDITION: Completely remove old antifouling paint, after all old antifouling paint has been completely removed, sanding the entire surface with 80 grit wet-or-dry sandpaper; wipe surface clean with Xylene¹ using the two-rag method before and after sanding. Apply two coats of ProGuard Ablative allowing for appropriate dry times.

BARE WOOD: Sand the entire surface with 80 grit wet-or-dry sandpaper; wipe surface clean with Xylene¹ using the two-rag method before and after sanding. Apply the first coat of ProGuard Ablative thinned 10% with Xylene². Apply two finish coats of ProGuard Ablative allowing for appropriate dry times.

UNDERWATER METALS: Apply an approved underwater metal primer as per manufacturer's instructions. Apply two coats of ProGuard Ablative allowing for appropriate dry times.

Do not use on aluminum.

MAINTENANCE

Antifouling are not effective under all conditions. Pollution, usage and natural occurrences can adversely affect an antifouling paint's performance. Therefore, we strongly suggest that the antifouling paints are checked regularly to make sure it is clean and that no growth is occurring. The less a boat is used, and the longer the idle periods are the higher the chance of fouling. Properly functioning antifouling paints will repel hard growth and requires only occasional light wiping with a soft cloth or Scotch-Brite™ pad to remove slime. Aggressive cleaning of antifouling paints, using tools such as scrubbing pads and brushes, will shorten the effective life of the paint, and should only be used if necessary.

¹ May not be an approved solvent for use in all areas.

² Thinning of this product may affect the V.O.C. compliance of this product.

Please consult your local government regulations for recommendations for volatile organic compound (VOC) limits.

PRECAUTIONARY STATEMENTS HAZARDS TO HUMANS AND DOMESTIC ANIMALS WARNING

Causes eye irritation. Harmful if absorbed through skin. Avoid contact with skin, eyes or clothing. Wear protective clothing such as gloves, long-sleeved cotton shirt, long pants and hat. May be fatal if swallowed or inhaled. Do not breathe vapor or spray mist. While spraying paint or sanding or sandblasting boat surfaces, wear a mask or a respirator jointly approved by the Mining Enforcement and Safety Administration and the National Institute for Occupational Safety and Health. Remove contaminated clothing and wash before reuse. Wash thoroughly with soap and water after handling.

FIRST AID

If Swallowed:

- Immediately call a poison control center or doctor
- Do not induce vomiting unless told to do so by a poison control center or doctor
- Do not give any liquid to the person
- Do not give anything by mouth to an unconscious person

If on skin or clothing:

- Take off contaminated clothing
- Rinse skin immediately with plenty of water for 15-20 minutes
- Call a poison control center or doctor for treatment advice

If inhaled:

- Move person to fresh air
- If person is not breathing, call 911 or an ambulance, then give artificial respiration, preferably mouth-to-mouth if possible
- Call a poison control center or doctor for further treatment advice

If in eyes:

- Hold eye open and rinse slowly and gently with water for 15-20 minutes
- Remove contact lenses, if present, after the first 5 minutes, then continue rinsing the eye
- Call a poison control center or doctor for treatment advice

Other: Have the product container or label with you when calling a poison control center or doctor or going for treatment.

Note to Physician: Contains petroleum distillate - vomiting may cause aspiration pneumonia.

ENVIRONMENTAL HAZARDS

This material is toxic to fish. Do not apply directly to water by cleaning of equipment or disposal of wastes. Do not allow chips and dust generated during paint removal to enter water. Dispose of paint debris in an approved landfill. Do not discharge effluent containing this product into lakes, streams, ponds, estuaries, oceans and other waters unless in accordance with the requirements of a National Pollution Discharge Elimination System (NPDES) permit and the permitting authority has been notified in writing prior to discharge. Do not discharge effluent to sewer systems without previously notifying the local sewage treatment plant authority. For guidance, contact your State Water Board or Regional Office of the EPA.

PHYSICAL OR CHEMICAL HAZARD

Flammable. Keep away from heat, sparks or open flames.

STORAGE AND DISPOSAL

Do not contaminate water, food or feed by storage or disposal. Open dumping is prohibited.

PESTICIDE DISPOSAL: Pesticide wastes are acutely hazardous. Improper disposal of excess pesticide, spray mixture or rinsate is a violation of Federal law. If these wastes cannot be disposed of by use according to label instructions, contact your State Pesticide or Environmental Control Agency, or the Hazardous Waste representative at the nearest EPA Regional Office for guidance.

CONTAINER DISPOSAL: Nonrefillable container. Do not reuse or refill this container. Triple rinse as follows: Empty the remaining contents into application equipment or a mix tank and drain for 10 seconds after the flow begins to drip. Fill the container ¼ full with water and recap. Shake for 10 seconds. Pour rinsate into application equipment or a mix tank or store rinsate for later use or disposal. Drain for 10 seconds after the flow begins to drip. Repeat this procedure two more times.

International Paint LLC
6001 Antoine Drive
Houston, TX USA
77091 • 713-682-1711

nauticalpaint.com

DISCLAIMER: The performance of any marine paint or coating depends on many factors outside the control of International Paint LLC, including surface preparation, proper application, and environmental conditions. Therefore, International Paint LLC cannot guarantee this product's suitability for your particular purpose or application. IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE AND OF MERCHANTABILITY ARE EXCLUDED. INTERNATIONAL PAINT LLC SHALL NOT, UNDER ANY CIRCUMSTANCES, BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES. By purchase or use of this product, buyer agrees that the sole and exclusive remedy, if any, is limited to the refund of the purchase price or replacement of the product at International Paint LLC's option.

NAUTICAL™

ANTIFOULING

PROGUARD ABLATIVE

Performance, value and reliability
Season-long protection in moderate to high fouling waters

**KEEP OUT OF REACH OF CHILDREN
WARNING**

SEE SIDE PANEL FOR ADDITIONAL
PRECAUTIONARY STATEMENTS



AkzoNobel

ACTIVE INGREDIENT:
CUPROUS OXIDE 41.97%
INERT INGREDIENTS 58.03%
100.00%
COPPER AS METALLIC 37.11%
CONTAINS PETROLEUM DISTILLATES
EPA EST. NO. 2693-TX-1
EPA REG NO. 2693-142



**NET CONTENTS:
ONE GALLON
(3.785 LITERS)**

RED NAU992

PROGUARD ABLATIVE

PRODUCT DESCRIPTION

ProGuard Ablative is performance, value and reliability all in one. ProGuard Ablative is an all-purpose, low V.O.C. antifouling paint formulated to erode away with use reducing paint build-up. ProGuard Ablative provides season-long protection in moderate to high fouling waters and can be applied directly over most properly prepared antifouling paints. Recommended for use on the underwater areas of fiberglass, wood, and properly primed metal (except aluminum) boat hulls and can be used in fresh, salt and brackish waters.

DIRECTIONS FOR USE

It is a violation of Federal Law to use this product in a manner inconsistent with its labeling. **NOTE:** Colors may fade or change above the waterline. Stir well before and during use, can be applied by brush, roller or spray. **Do not use on aluminum.**

COMPATIBILITY: ProGuard Ablative can be applied over most other antifouling paints provided the old coating is tightly adhered, is in sound condition and has been thoroughly sanded with 80 grit wet-or-dry sandpaper.

V.O.C.: Less than 330 grams/liter (2.75lbs./gal.)

THEORETICAL COVERAGE: 455 sq. ft./gal at 3.6 mils WFT and 2 mils DFT.

CLEAN UP: Acetone or Xylene¹.

THINNER: Xylene² (thin only when necessary, do not exceed 10% by volume).

APPLICATION TEMPERATURE: 50°F (10°C)* and above (air and hull).

*If the air temperature falls below 50° F (10° C) during the dry time extend the dry times by 12 hours minimum.

ESTIMATED DRY TIMES:

Temp °F (°C)	Touch Dry	Overcoating Time		
		Minimum	Minimum	Maximum
50°F (10°C)	3 Hours	12 Hours	16 Hours	60 Days
77°F (25°C)	2 Hours	6 Hours	16 Hours	60 Days
95°F (35°C)	1 Hour	4 Hours	16 Hours	60 Days

PREPARATION/APPLICATION

BARE FIBERGLASS: Scrub the surface thoroughly with a stiff brush using soap and water. Flush with fresh water to remove the soap residue and allow surface to dry. Remove mold release wax and surface contamination by wiping down the surface with Xylene¹ using the two-rag method. Fill any surface imperfections with approved filler for underwater use. Sand the entire surface with 80-grit sandpaper until a flat matte finish is obtained. Wipe the sanding residue off the surface with Xylene¹ using the two-rag method. Apply two coats of ProGuard Ablative allowing for appropriate dry times.

PREVIOUSLY PAINTED SURFACE - GOOD CONDITION: Remove all traces of loose paint by sanding the entire surface with 80 grit wet-or-dry sandpaper; wipe surface clean with Xylene¹ using the two-rag method before and after sanding. Apply two coats of ProGuard Ablative allowing for appropriate dry times.

PREVIOUSLY PAINTED SURFACE - POOR CONDITION: Completely remove old antifouling paint, after all old antifouling paint has been completely removed, sanding the entire surface with 80 grit wet-or-dry sandpaper; wipe surface clean with Xylene¹ using the two-rag method before and after sanding. Apply two coats of ProGuard Ablative allowing for appropriate dry times.

BARE WOOD: Sand the entire surface with 80 grit wet-or-dry sandpaper; wipe surface clean with Xylene¹ using the two-rag method before and after sanding. Apply the first coat of ProGuard Ablative thinned 10% with Xylene². Apply two finish coats of ProGuard Ablative allowing for appropriate dry times.

UNDERWATER METALS: Apply an approved underwater metal primer as per manufacturer's instructions. Apply two coats of ProGuard Ablative allowing for appropriate dry times.

Do not use on aluminum.

MAINTENANCE

Antifouling are not effective under all conditions. Pollution, usage and natural occurrences can adversely affect an antifouling paint's performance. Therefore, we strongly suggest that the antifouling paints are checked regularly to make sure it is clean and that no growth is occurring. The less a boat is used, and the longer the idle periods are the higher the chance of fouling. Properly functioning antifouling paints will repel hard growth and requires only occasional light wiping with a soft cloth or Scotch-Brite™ pad to remove slime. Aggressive cleaning of antifouling paints, using tools such as scrubbing pads and brushes, will shorten the effective life of the paint, and should only be used if necessary.

¹ May not be an approved solvent for use in all areas.

² Thinning of this product may affect the V.O.C. compliance of this product.

Please consult your local government regulations for recommendations for volatile organic compound (VOC) limits.

PRECAUTIONARY STATEMENTS HAZARDS TO HUMANS AND DOMESTIC ANIMALS WARNING

Causes eye irritation. Harmful if absorbed through skin. Avoid contact with skin, eyes or clothing. Wear protective clothing such as gloves, long-sleeved cotton shirt, long pants and hat. May be fatal if swallowed or inhaled. Do not breathe vapor or spray mist. While spraying paint or sanding or sandblasting boat surfaces, wear a mask or a respirator jointly approved by the Mining Enforcement and Safety Administration and the National Institute for Occupational Safety and Health. Remove contaminated clothing and wash before reuse. Wash thoroughly with soap and water after handling.

FIRST AID

If Swallowed:

- Immediately call a poison control center or doctor
- Do not induce vomiting unless told to do so by a poison control center or doctor
- Do not give any liquid to the person
- Do not give anything by mouth to an unconscious person

If on skin or clothing:

- Take off contaminated clothing
- Rinse skin immediately with plenty of water for 15-20 minutes
- Call a poison control center or doctor for treatment advice

If inhaled:

- Move person to fresh air
- If person is not breathing, call 911 or an ambulance, then give artificial respiration, preferably mouth-to-mouth if possible
- Call a poison control center or doctor for further treatment advice

If in eyes:

- Hold eye open and rinse slowly and gently with water for 15-20 minutes
- Remove contact lenses, if present, after the first 5 minutes, then continue rinsing the eye
- Call a poison control center or doctor for treatment advice

Other: Have the product container or label with you when calling a poison control center or doctor or going for treatment.

Note to Physician: Contains petroleum distillate - vomiting may cause aspiration pneumonia.

ENVIRONMENTAL HAZARDS

This material is toxic to fish. Do not apply directly to water by cleaning of equipment or disposal of wastes. Do not allow chips and dust generated during paint removal to enter water. Dispose of paint debris in an approved landfill. Do not discharge effluent containing this product into lakes, streams, ponds, estuaries, oceans and other waters unless in accordance with the requirements of a National Pollution Discharge Elimination System (NPDES) permit and the permitting authority has been notified in writing prior to discharge. Do not discharge effluent to sewer systems without previously notifying the local sewage treatment plant authority. For guidance, contact your State Water Board or Regional Office of the EPA.

PHYSICAL OR CHEMICAL HAZARD

Flammable. Keep away from heat, sparks or open flames.

STORAGE AND DISPOSAL

Do not contaminate water, food or feed by storage or disposal. Open dumping is prohibited.

PESTICIDE DISPOSAL: Pesticide wastes are acutely hazardous. Improper disposal of excess pesticide, spray mixture or rinsate is a violation of Federal law. If these wastes cannot be disposed of by use according to label instructions, contact your State Pesticide or Environmental Control Agency, or the Hazardous Waste representative at the nearest EPA Regional Office for guidance.

CONTAINER DISPOSAL: Nonrefillable container. Do not reuse or refill this container. Triple rinse as follows: Empty the remaining contents into application equipment or a mix tank and drain for 10 seconds after the flow begins to drip. Fill the container ¼ full with water and recap. Shake for 10 seconds. Pour rinsate into application equipment or a mix tank or store rinsate for later use or disposal. Drain for 10 seconds after the flow begins to drip. Repeat this procedure two more times.

International Paint LLC
6001 Antoine Drive
Houston, TX USA
77091 • 713-682-1711

nauticalpaint.com